

Steel	Chemical Composition				
	C % (m/m)	Si % (m/m)	Mn % (m/m)	P % (m/m)	S % (m/m)
080A42	0,40 to 0,45	0,10 to 0,40	0,70 to 0,90	0,05 max	0,05 max