

Steel	Chemical Composition				
	C % (m/m)	Si % (m/m)	Mn % (m/m)	P % (m/m)	S % (m/m)
210M15	0,12 to 0,18	0,10 to 0,40	0,90 to 1,30	0,05 max	0,10 to 0,18