

Steel	Chemical Composition					
	C % (m/m)	Si % (m/m)	Mn % (m/m)	P % (m/m)	S % (m/m)	Pb % (m/m)
212A42	0,40 to 0,45	0,25 max	1,00 to 1,30	0,06 max	0,12 to 0,20	-